



# Flash-Vent™ SA

## Self-Adhering Stainless Steel Drainage Plane Flashing

### Key Properties

- Type 304 (standard) & Type 316 stainless steel for more corrosive or coastal areas
- 20-year warranty
- Co-polymer butyl adhesive
- Does not clog with mortar
  - Eliminates the need for mortar netting
- Best in class puncture resistance
- Mold resistant: passes ASTM D3273
- Made of 60% recycled stainless steel ♻️
- HPD available

### Uses

- Cavity wall
- Stucco
- Manufactured stone
- Thin brick
- Compatible with:
  - Air barriers
  - Spray polyurethane foam
  - Cavity wall insulations
  - Construction sealants



Available in:  
12", 18", 24", 36" x 40' Custom sizes upon request.

### Description

Flash-Vent™ SA has been designed with a flexible 2 mil sheet of Type 304 stainless steel, 10 mils of butyl adhesive with a siliconized release liner, and drainage fabric laminated to one side.

### Application

**Important!** Always apply the flashing with the soft drainage surface facing up and to the outside. Flashing must make it to the leading edge of the cladding. Do not apply the membrane to a substrate that has absorbed water. Self-adhering membranes must be rolled with a suitable hard roller to ensure the entire membrane is pressed firmly into the substrate. Apply an approved sealant to all termination edges, laps, cuts, and penetrations.

**Horizontal Masonry Surfaces:** Flashing shall be installed on a clean, dry, and smooth substrate, then a fresh bed of mortar will be placed on top of the flashing. Flashing shall be trimmed flush with the exterior face of the wall.

**Vertical Masonry and Concrete Surfaces:** Apply flashing with drainage surface facing up and to the outside. Terminate in one of the following ways:

- Use a termination bar to fasten the flashing to the backer wall and seal the top edge with an approved sealant.
- Use other methods indicated in the drawings.

**Foundation Sill Flashing:** Flashing width is required to be trimmed flush with the outside face of the exterior wythe, extend through the cavity, and rise a height on the inside not less than 8". Install the material on the backer wall using a technique indicated above in Vertical Masonry and Concrete Surfaces paragraph. Then, lay the flashing for foundation sills in a bed of approved sealant and top with a fresh bed of mortar. Where sill and column meet, flashing shall be brought a minimum of 10" up the column and be sealed with an approved sealant.

**Cavity Wall Flashing:** Flashing width is required to be trimmed flush with the outside face of the exterior wythe, extend through the cavity, and rise the height to cross the cavity and extend up the backer wall at least 8", the rising height required to extend above lintel steel is at least 6". Install on the backer wall using a technique indicated above in Vertical Masonry and Concrete Surfaces paragraph. Flashing for exterior wythe shall be topped with a fresh bed of mortar.

**Shelf Angle Flashing:** Shelf Angle flashing shall be trimmed flush with the outside toe of the shelf angle, go up the face of the beam, and then through the wall turning up on the inside not less than 2".

**Parapets or Copings:** Flashing for parapets or copings shall be topped with a fresh bed of mortar. Flashing shall be trimmed flush with the exterior and interior faces of the masonry wall.

**Head and Sill Flashing:** The flashing shall be trimmed flush with the outside of the wall or lintel angle and then carried through or up the wall as indicated. Flashing shall extend 6" beyond each side of the opening and be turned up at the sides to create end dams.

**Joining of Materials:** Flashing must be butted together over a splice piece of 4" or greater of the York 304 SA. York 304 SA should be applied with stainless steel facing up. This creates a continuous adhesive backing to the flashing. (Overlapping is not an acceptable practice with drainage plane flashing.)

**Corners and End Dams:** Corners and end dams can be made per instructions on York's website ([www.yorkflashings.com](http://www.yorkflashings.com)) or use York's preformed corners and end dams. End dams shall be folded, not cut.

**Primer:** Not necessary in most applications, when applied to a clean dry surface. Field test surfaces to ensure appropriate adhesion. On surfaces that need additional adhesion, prime surface with an approved flashing primer. Allow primer to dry completely before installing flashing.

## Preparation

All masonry surfaces receiving through-wall flashings shall be free from loose materials, and reasonably smooth. There shall be no slopes that will form pockets or prevent free drainage of water to the exterior surfaces of the wall. All work shall be executed in conformance with accepted trade practice.

## TECHNICAL DATA

### FLASH-VENT™ SELF-ADHERING STAINLESS STEEL

Properties	Flash-Vent™ SA Stainless Steel
<b>Base Material</b>	<b>Stainless Steel</b>
<b>Base Material Recycled Content</b>	60% - 70%
<b>Recyclable</b>	Yes
<b>Warranty</b>	20 year
<b>Lap Joints in 100'</b>	17
<b>Fire Resistant (ASTM E84)</b>	Class A
<b>Mold Resistant (ASTM D3273)</b>	Yes
<b>Tensile Strength (ASTM D412)</b>	100,000+
<b>Puncture Resistance (ASTM E154)</b>	2,500+ psi
<b>Chemically Compatible with All Wall Components</b>	Yes
<b>Gap Spanability</b>	Width of cavity
<b>Primer Required</b>	No
<b>Adhesion</b>	9 psi
<b>Application Temperature</b>	20° F to 170° F

